

MASTERFLEX® Tubing Chemical Compatibility Tables

Determine the right tubing formulation for your application using the chemical compatibility tables at right. These tables are for use with all Masterflex tubing sizes. All ratings in the tables indicate tubing condition after exposure to the chemical at 21°C (70°F).

Ratings & Materials Legend

Ratings

- A:** No effect; little noticeable change
- B:** Minor effect; slight corrosion or discoloration
- C:** Moderate effect; not recommended for continuous use; softening, loss of strength, swelling and/or shrinkage
- D:** Severe effect; not recommended for use; severe softening, swelling and/or shrinkage
- :** No data available

Tubing formulations

- PN:** PharMed® BPT, High-Pressure PharMed® BPT, PharmaPure®, Norprene®, Norprene Food
- CF:** C-FLEX®
- S:** Silicone (peroxide/platinum-cured), BioPharm, BioPharm Plus, Style 100 RF Silicone
- T:** Tygon® Lab, Tygon LFL, Tygon Food
- TU:** Tygon Fuel & Lubricant
- TC:** Tygon Chemical
- CS:** Style 500 RF FFKM
- V:** Viton®, FDA Viton
- PT:** Polytetrafluoroethylene (PTFE)

Pump head materials

- PSF:** Polysulfone
- PC:** Polycarbonate
- PPS:** Polyphenylene sulfide
- SS:** Stainless steel
- PP:** Polypropylene

Fluid	Tubing formulation									Pump head material				
	PN	CF	S	T	TU	CS	TC	V	PT	PSF	PC	PPS	SS	PP
Acetaldehyde	D	A	B	D	D	A	D	D	A	D	—	A	A	A
Acetate LMW	A	A	—	D	D	—	C	—	A	D	—	A	A	A
Acetic acid <5%	A	A	A	A	A	A	B	—	A	A	A	A	B	B
Acetic acid >5%	A	A	A	B	A	A	B	B	A	A	A	A	B	A
Acetic anhydride	A	B	C	D	D	A	A	D	A	D	C	A	B	C
Acetone	D	C	C	D	D	A	C	D	A	D	D	A	A	A
Acetonitrile	B	A	—	D	D	—	B	D	A	D	D	A	A	—
Acetyl bromide	C	A	—	D	D	—	C	—	A	—	—	—	—	—
Acetyl chloride	C	A	C	D	D	A	C	A	A	D	D	A	A	D
Air	A	A	A	A	A	A	A	A	A*	A	A	A	A	A
Aliphatic hydrocarbons	D	D	—	D	B	—	D	—	—	—	—	—	B	—
Aluminum chloride	A	A	B	A	A	—	A	A	A	A	A	A	D	A
Aluminum sulfate	A	A	A	A	A	—	A	A	A	A	A	A	D	A
Alums	A	A	A	A	A	—	A	A	A	—	—	—	—	A
Ammonia, gas / liquid	A	A	C	B	B	—	B	D	A	A	D	A	B	A
Ammonium acetate	A	A	—	A	A	A	A	D	A	—	A	—	B	A
Ammonium carbonate	A	A	C	A	A	A	A	A	A	A	—	A	B	A
Ammonium chloride	A	A	C	A	A	A	A	A	A	A	—	A	C	A
Ammonium hydroxide	A	A	A	B	C	A	A	B	A	A	D	A	A	A
Ammonium nitrate	A	A	C	A	A	A	A	A	A	A	—	A	A	A
Ammonium phosphate	A	A	A	A	A	A	A	A	A	A	A	A	B	A
Ammonium sulfate	A	A	A	A	A	A	A	A	A	A	A	A	B	A
Amyl acetate	B	D	D	D	D	B	D	D	A	D	D	A	A	D
Amyl alcohol	D	D	D	D	A	A	A	A	A	A	—	A	A	A
Amyl chloride	C	D	D	D	D	—	D	A	A	D	D	D	A	D
Aniline	C	B	D	D	D	A	D	B	A	D	D	A	A	A
Aniline hydrochloride	C	B	D	D	D	A	D	B	A	—	D	—	D	D
Aqua regia (80% HCl, 20% HNO3)	D	—	D	D	D	—	A	B	A	D	D	D	D	B
Aromatic hydrocarbons	D	D	—	D	D	—	D	A	—	—	—	—	B	—
Arsenic salts	A	—	—	A	A	—	A	D	—	—	—	—	—	—
Barium salts	A	A	A	A	A	A	A	A	A	A	—	A	B	B
Benzaldehyde	D	D	B	D	D	A	C	D	A	C	C	A	B	C
Benzenesulfonic acid	D	A	D	D	D	A	D	A	A	D	D	A	B	D
Bleaching liquors	A	B	B	A	A	—	A	A	A	—	—	—	—	B
Boric acid	A	A	A	A	A	A	A	A	A	A	A	A	B	A
Bromine	D	A	D	D	D	—	D	A	A	—	D	D	D	C
Butane	A	D	D	A	A	B	B	A	A	—	—	A	A	B
Butanol (butyl alcohol)	D	B	B	D	A	A	A	A	A	A	C	A	A	B
Butyl acetate	B	D	D	D	D	B	D	D	A	D	D	A	B	D
Butyric acid	B	A	D	D	C	A	D	B	A	—	—	A	B	C
Calcium oxide	A	—	A	A	A	—	A	A	A	—	—	—	A	A
Calcium salts	A	A	B	A	A	A	A	A	A	A	—	—	A	A
Carbon bisulfide	D	D	D	D	D	—	D	—	A	—	—	—	A	C
Carbon dioxide	A	A	B	A	A	A	A	A	A*	—	A	A	A	A
Carbon tetrachloride	D	B	D	D	D	B	D	A	A	A	D	A	B	D
Chlorine, dry	C	A	D	A	A	—	C	A	A*	D	—	D	A	D
Chlorine, wet	D	A	D	B	A	—	C	B	A	D	—	D	C	D
Chloroacetic acid	B	A	—	A	D	B	A	D	A	D	D	A	B	D
Chlorobenzene	D	D	D	D	D	A	D	A	B	D	D	A	A	D
Chlorobromomethane	B	D	D	D	D	—	A	A	A	D	—	—	—	A
Chloroform	C	D	D	D	D	B	D	A	A	D	D	A	A	D
Chlorosulfonic acid	D	A	D	D	D	A	D	D	A	D	—	—	D	D
Chromic acid, 30%	A	A	C	B	C	—	B	A	A	D	D	A	B	A
Chromium salts	A	A	—	A	A	—	A	—	—	—	—	—	—	—
Copper salts	A	A	A	A	A	—	A	A	A	—	—	A	B	A
Cresol	D	D	D	D	C	A	A	A	A	D	D	A	A	C
Cyclohexane	D	D	D	D	C	B	D	A	A	A	B	A	A	D
Cyclohexanone	D	D	D	D	D	—	C	D	A	D	D	A	A	D
Diacetone alcohol	A	A	B	D	D	A	A	D	A	—	D	—	B	C
Dimethyl formamide	B	B	B	D	D	A	A	D	A	D	D	A	A	A
Essential oils	D	B	C	D	C	—	D	—	—	—	—	—	—	—
Ethanol (ethyl alcohol)	C	B	A	D	B	A	A	A	A	B	B	A	A	A
Ether	C	D	D	D	C	B	D	D	A	D	D	A	A	B
Ethyl acetate	B	D	B	D	D	A	D	D	A	A	D	A	B	A
Ethyl bromide	D	A	D	D	D	—	C	A	A	—	—	—	—	D
Ethyl chloride	C	A	D	D	D	—	D	A	A	D	D	—	A	D
Ethylamine	D	A	C	D	D	B	B	D	—	—	—	—	—	—
Ethylene chlorohydrin	A	A	C	D	B	—	A	A	A	D	D	A	B	D
Ethylene dichloride	C	A	D	D	D	B	D	A	A	D	D	A	B	A
Ethylene glycol	A	B	A	A	A	A	A	A	A	A	C	A	B	A
Ethylene oxide	A	A	D	A	A	B	A	D	A	A	D	D	B	D
Fatty acids	C	B	C	B	B	A	C	A	A	—	C	—	B	A
Ferric chloride	A	A	B	A	A	—	A	A	A	A	—	A	D	A
Ferric sulfate	A	A	B	A	A	A	A	A	A	A	—	A	B	A
Ferrous chloride	A	A	C	A	A	—	A	A	A	A	D	A	D	A
Ferrous sulfate	A	A	C	A	A	—	A	A	A	A	A	A	B	A
Fluoboric acid	D	A	A	A	D	—	A	—	A	A	—	A	B	A
Fluoroborate salts	A	A	—	A	A	—	A	—	—	—	—	—	—	—
Fluosilicic acid	C	A	D	A	A	—	A	A	A	A	—	A	C	A
Formaldehyde	D	A	B	D	D	A	C	D	A	A	A	A	C	A
Formic acid, 25%	A	A	B	A	C	A	A	D	A	C	D	A	B	A
Freon® TMS	D	C	—	D	D	D	A	—	A	—	D	A	—	—
Gasoline, high-aromatic	D	D	D	D	B	B	D	A	B	A	C	A	A	D
Gasoline, nonaromatic	D	D	D	D	B	B	D	A	A	A	A	A	—	C
Glucose	A	A	A	A	A	A	A	A	A	—	A	—	A	A
Glue, P.V.A.	A	A	A	A	A	—	A	—	A	—	—	—	A	C
Glycerin	A	B	A	A	A	—	A	A	A	A	A	A	A	A
Hydriodic acid	D	A	—	A	A	—	A	A	—	—	—	—	—	—
Hydrobromic acid, 30%	D	A	D	A	A	—	A	A	A	B	D	A	D	A
Hydrochloric acid (dil)	A	A	D	A	A	—	A	A	A	A	A	D	D	A
Hydrochloric acid (med)	B	A	D	A	D	A	A	A	A	A	D	D	D	A
Hydrochloric acid (conc)	—	B	D	A	D	A	A	A	A	A	B	D	D	A
Hydrocyanic acid	A	A	C	A	A	A	A	A	A	—	—	—	B	A
Hydrocyanic acid, gas, 10%	A	A	C	A	A	—	A	A	A	—	—	—	—	A
Hydrofluoric acid, 50%	D	A	D	C	D	D	A	D	A	—	D	A	D	C
Hydrofluoric acid, 75%	—	A	D	D	D	—	D	—	A	—	D	A	D	C

Do not use the P/S PTFE-tubing pump head with gases due to excessive heat buildup.

⚠ DANGER

Even if tubing passes the immersion test, variations in temperature, pressure, or concentration may cause tubing failure. SERIOUS INJURY MAY RESULT.

Use suitable guards and/or personal protection when pumping chemicals.

⚠ WARNING

The information in these tables has been supplied by the tubing manufacturers and is to be used ONLY as a guide to select your tubing. Test fluids and tubing using the tubing test procedure below. No warranty (neither express or implied) is given that the information in these tables is accurate or complete or that any material is suitable for any purpose.

Tubing Test Procedure

- 1. Measure and weigh a sample of tubing.**
- 2. Immerse the sample in the fluid for 72 hours in a closed vessel.**
- 3. Dry sample, then measure and weigh it. Inspect carefully for signs of deterioration such as swelling, embrittlement, cracking, softness, or change of size or weight.**
- 4. If there is no sign of deterioration, test a sample in pump under the conditions of your application.**

MASTERFLEX® Tubing Chemical Compatibility Tables (cont.)

Fluid	Tubing formulation										Pump head material				
	PN	CF	S	T	TU	CS	TC	V	PT	PSF	PC	PPS	SS	PP	
Hydrogen peroxide (dil)	A	A	A	A	A	A	A	A	A	A	A	—	B	A	
Hydrogen peroxide, 90%	B	D	A	D	D	A	B	A	A	A	A	—	B	—	
Hypochlorous acid	A	A	D	A	A	A	A	A	A	—	—	—	—	—	
Iodine solutions	A	C	C	A	A	—	A	A	A	—	D	D	D	A	
Iodoform	—	—	—	—	—	—	—	C	A	—	—	—	A	—	
Kerosene	D	D	D	D	B	A	D	A	A	A	A	A	A	A	
Ketones	D	B	—	D	D	—	C	—	A	D	D	A	A	A	
Lacquer solvents	B	D	D	D	D	A	D	D	A	A	D	—	A	D	
Lactic acid, 3-10%	A	A	A	A	A	A	A	A	A	A	A	A	B	A	
Lead acetate	A	A	D	A	A	—	A	D	A	A	—	A	B	A	
Linseed oil	C	D	A	D	A	A	B	A	A	A	—	A	A	A	
Lithium hydroxide	B	A	D	A	A	—	—	C	A	—	D	A	B	—	
Magnesium chloride	A	A	A	A	A	A	A	A	A	A	A	A	B	A	
Magnesium sulfate	A	A	A	A	A	A	A	A	A	A	A	A	B	A	
Malic acid	A	A	B	A	A	A	A	A	A	—	—	—	A	B	
Manganese salts	A	A	B	A	A	—	A	A	A	—	—	—	D	—	
Mercury salts	A	A	—	A	A	—	A	A	A	—	—	—	B	A	
Methane	A	D	D	A	A	B	A	A*	—	—	—	—	A	B	
Methanol (methyl alcohol)	D	—	A	C	C	A	A	B	A	D	B	A	A	A	
Methyl chloride	C	A	D	D	D	B	D	B	A	D	—	A	A	D	
Methyl ethyl ketone (MEK)	D	—	D	D	D	B	C	D	A	D	D	A	A	A	
Mixed acid (40% H ₂ SO ₄ , 15% HNO ₃)	B	—	—	B	D	—	—	—	A	D	—	—	B	A	
Molybdenum disulfide	—	A	—	—	—	—	—	A	—	—	—	—	—	—	
Monoethanolamine	C	B	B	D	D	—	D	A	A	A	—	A	A	B	
Naphtha	D	D	D	D	B	B	D	A	B	B	—	A	A	A	
Natural gas	A	D	A	A	A	B	A	A	A*	—	—	—	A	B	
Nickel salts	A	A	A	A	A	A	A	A	A	A	—	A	B	A	
Nitric acid (dil)	A	A	B	A	D	A	A	B	A	A	B	A	A	A	
Nitric acid (med)	A	—	C	A	D	A	A	A	A	C	C	D	A	B	
Nitric acid (conc)	D	—	D	D	D	A	A	A	A	C	D	D	A	C	
Nitrobenzene	D	D	D	D	D	A	D	B	A	D	D	A	B	—	
Nitrogen oxides	A	A	D	A	A	—	A	D	A	—	—	—	—	—	
Nitrous acid	A	A	—	A	C	—	A	—	A	—	—	—	B	A	
Oils, animal	C	B	B	D	B	—	B	A	A	—	—	—	A	—	
Oils, mineral	D	B	B	C	A	—	D	A	A	B	A	—	A	A	
Oils, vegetable	C	B	B	D	A	A	B	A	A	A	—	—	A	A	
Oleic acid	C	A	D	D	B	A	D	B	A	A	A	A	B	A	
Oxalic acid, cold	B	A	B	B	D	A	A	A	A	—	B	A	B	A	
Oxygen, gas	A	A	B	A	A	A	A	B	A*	A	A	—	A	—	
Palmitic acid, 100% in ether	C	—	D	D	B	A	C	A	A	—	—	—	B	C	
Perchloric acid	A	A	D	C	D	A	A	A	A	D	D	A	C	C	
Perchloroethylene	C	B	D	D	D	B	D	A	A	D	D	A	B	D	
Phenol (carbolic acid)	A	D	D	B	C	A	A	A	A	—	D	—	B	A	
Phosphoric acid, 50%	A	A	C	A	A	A	A	A	A	A	B	—	A	A	
Phthalic acid	A	D	B	D	A	—	A	B	A	—	—	—	B	A	
Plating solutions	A	A	D	A	D	—	A	A	A	—	—	—	—	A	
Polyglycol	B	B	A	A	A	—	—	A	—	—	—	—	—	A	
Potassium carbonate	A	A	—	A	A	A	A	A	—	A	—	A	B	A	
Potassium chlorate	B	A	B	A	A	A	—	A	A	—	A	—	A	B	
Potassium hydroxide (med)	A	A	B	A	D	B	—	D	A	A	D	A	B	A	
Potassium hydroxide (conc)	A	A	C	D	D	B	—	D	A	A	—	—	B	B	
Potassium iodide	A	A	—	A	A	—	—	A	A	—	—	—	A	B	
Propanol (propyl alcohol)	C	—	A	D	D	A	A	A	A	B	D	A	A	A	
Pyridine	C	A	D	D	D	A	C	D	A	D	D	A	A	B	
Silicone fluids	A	B	C	B	A	—	B	A	A	—	—	A	A	A	
Silicone oils	C	B	C	B	A	—	B	A	A	—	A	A	A	A	
Silver nitrate	A	A	A	A	A	A	A	A	A	A	A	A	B	A	
Soap solutions	B	A	A	A	A	A	A	A	A	A	A	A	A	A	
Sodium bicarbonate	A	A	A	A	A	A	A	A	A	A	A	A	B	A	
Sodium bisulfate	A	A	—	A	A	A	A	A	A	A	A	A	D	A	
Sodium bisulfite	A	A	A	A	A	A	—	A	A	—	A	—	B	A	
Sodium borate	A	A	A	A	A	—	—	A	A	A	A	A	B	B	
Sodium carbonate	A	A	A	A	A	A	A	A	A	A	A	A	A	A	
Sodium chlorate	A	A	C	A	A	—	A	A	A	A	A	A	B	A	
Sodium chloride	A	A	A	A	A	A	A	A	A	A	A	A	C	A	
Sodium ferrocyanide	A	A	—	B	B	—	—	A	A	—	—	—	B	A	
Sodium hydrosulfite	B	A	—	A	A	—	—	—	A	—	—	—	—	—	
Sodium hydroxide (dil)	A	A	A	A	D	A	A	A	A	A	D	A	A	A	
Sodium hydroxide, 25%	A	B	B	C	D	—	A	A	A	A	D	A	B	A	
Sodium hydroxide (conc)	—	C	—	C	D	—	A	A	A	—	D	A	C	B	
Sodium hypochlorite, <5%	A	A	B	A	A	A	A	A	A	A	B	A	A	A	
Sodium hypochlorite, >5%	A	A	B	A	A	A	A	A	A	A	—	A	C	B	
Sodium nitrate	A	A	D	A	A	A	A	A	A	—	—	—	B	A	
Sodium silicate	A	A	A	A	A	A	—	A	A	—	—	A	B	A	
Sodium sulfide	A	A	A	A	A	A	A	A	A	A	—	A	C	A	
Sodium sulfite	A	A	A	A	A	A	A	A	A	—	D	—	A	B	
Steam, up to 40 psi	C	—	A	D	D	A	—	B	A*	A	A	A	—	—	
Stearic acid	C	A	B	A	B	A	C	A	A	C	A	—	B	C	
Styrene	D	D	D	D	D	A	D	A	A	—	D	—	A	—	
Sulfuric acid (dil)	A	A	D	A	A	A	A	A	A	A	A	A	D	A	
Sulfuric acid (med)	A	A	D	A	B	—	A	A	A	B	C	A	D	A	
Sulfuric acid (conc)	D	A	D	D	D	C	—	D	A	D	D	A	C	B	
Sulfurous acid	A	A	D	A	A	—	A	B	A	A	—	A	B	A	
Tannic acid	B	A	B	B	D	—	—	A	A	—	—	A	B	A	
Tanning liquors	A	B	—	A	A	—	—	A	A	—	—	—	A	B	
Tartaric acid	A	A	A	A	A	A	A	A	A	A	B	A	C	A	
Tin salts	A	A	B	A	A	—	A	—	A	—	—	—	—	A	
Toluene (toluol)	D	D	D	D	D	A	D	A	A	D	D	A	A	B	
Trichloroacetic acid	B	A	D	A	D	—	—	A	C	A	—	D	A	A	
Trichloroethylene	D	D	D	D	D	B	D	A	A	C	D	A	B	D	
Trisodium phosphate	A	A	—	A	A	—	—	A	A	A	—	A	B	A	
Turpentine	D	D	D	D	B	A	D	A	A	—	—	—	A	B	
Urea	A	A	B	A	A	A	—	A	—	C	D	A	A	A	
Uric acid	A	A	—	A	C	—	A	—	A	—	—	—	B	A	
Water, fresh	A	A	B	A	A	A	A	A	A	A	A	A	A	A	
Water, salt	A	A	A	A	A	A	A	A	A	A	A	A	B	A	
Xylene	D	D	D	D	D	A	D	A	A	D	D	A	A	C	
Zinc chloride	A	A	A	A	A	A	A	A	A	A	A	A	D	A	

*Do not use the P/S® PTFE-tubing pump head with gases due to excessive heat buildup.

Ratings & Materials Legend

Ratings

- A:** No effect; little noticeable change
- B:** Minor effect; slight corrosion or discoloration
- C:** Moderate effect; not recommended for continuous use; softening, loss of strength, swelling and/or shrinkage
- D:** Severe effect; not recommended for use; severe softening, swelling and/or shrinkage
- :** No data available

Tubing formulations

- PN:** PharMed® BPT, High-Pressure PharMed® BPT, PharmaPure®, Norprene®, Norprene Food
- CF:** C-FLEX®
- S:** Silicone (peroxide/platinum-cured), BioPharm, BioPharm Plus, Style 500 RF Silicone
- T:** Tygon® Lab, Tygon LFL, Tygon Food
- TU:** Tygon Fuel & Lubricant
- TC:** Tygon Chemical
- CS:** CHEM-SURE®
- V:** Viton®, FDA Viton
- PT:** Polytetrafluoroethylene (PTFE)

Pump head materials

- PSF:** Polysulfone
- PC:** Polycarbonate
- PPS:** Polyphenylene sulfide
- SS:** Stainless steel
- PP:** Polypropylene

Tubing for Food Products

Liquified food products	Norprene® Food	Silicone	Tygon® food
Alcohol	B	—	—
Beer	B	A	—
Brandy	B	—	—
Butter	A	B	A
Carrot	A	—	A
Chocolate syrup	A	—	A
Citric acid	A	A	A
Coffee	A	A	—
Corn oil	—	A	—
Corn syrup	—	—	A
Fish	—	A	A
Fruit juices	A	—	A
Liqueurs	B	B	—
Mayonnaise	A	—	A
Milk	A	A	A
Milk of magnesia	A	—	B
Molasses	A	—	—
Orange syrup	A	B	—
Sauerkraut	A	—	B
Shortening (liquid)	C	B	—
Soft drink concentrate	B	C	—
Sugar	A	A	A
Tomatoes	A	—	A
Vegetable oil	B	B	B
Vinegar	A	A	A
Whiskey	B	A	B
Wines	B	A	B